

Properties	Unit	TP4204	TP4207	TP4208	TP4209	TP4210	TP4407	TP3403	TP6603	TP6802
相對黏度 Relative Viscosity	-	2.36±0.05	2.45±0.05	2.45±0.05	2.55±0.05	2.55±0.05	2.70±0.05	2.80±0.05	3.30±0.10	4.00±0.10
拉伸強度 Tensile Strength at Yield	kgf/cm <sup>2</sup>	781	626	652	649	713	647	670	784	782
拉伸伸長率 Tensile Elongation at Yield	%	4.9	4.7	4.8	4.6	4.3	5.3	4.6	4.0	4.5
斷裂強度 Tensile Strength at Break	kgf/cm <sup>2</sup>	434	512	511	532	417	498	466	761	764
斷裂伸長率 Tensile Elongation at Break	%	125	327	309	331	55	307	326	328	331
彎曲強度 Flexural Strength	kgf/cm <sup>2</sup>	1109	976	998	1020	1054	956	1072	902	1042
彎曲模數 Flexural Modulus	kgf/cm <sup>2</sup>	27008	23721	23655	24237	25211	22708	24452	21760	22657
熔點 Melting Point	°C	224	224	224	224	224	224	220	225	225
融熔流動率 Melt Flow Index	g/min	240	174	230	145	172	98	95	30 ~ 60	15 ~ 35

※ Condition : 40HR / 23°C / 50% RH

※ Mechanical properties are for reference only.

Packaging: 780 kgs Jumbo Bag <15.6mt / 20' Container>

25 kgs Paper Bag <15.0mt / 20' Container>